



Registration Certificate

Carpet Name: SAVOIR FAIRE INTERFACE

Licensee: INTERFACE

Licence Number: 1016

Label Number: 24315

ACCS Contract Grading: CEHD 4*

ACCS Residential Grading: NONE

Suitable for Stairs: Yes

Date Graded: 24-01-2024



Andrew Martin
Secretary ACCS



Administered by the Carpet Institute of Australia Limited ABN 11 006 829 303

PO Box 7172, St Kilda Road, Melbourne Victoria 3004 Tel: (03) 9804 5559

Email: info@carpetoz.com.au • www.carpetinstitute.com.au

This certificate remains the property of the Carpet Institute of Australia Limited.

Carpet Details:**Company: INTERFACE****Label No: 24315****Licence No: 1016****Office No: 7494****Names:**

SAVOIR FAIRE INTERFACE

Details:

Awarded Res Grade: NONE
 Awarded Con Grade: CEHD 4*
 Registered On: 24/01/2024
 Active: Yes
 Date In-Active:
 Manufacture Method: Tufted
 Twist Set: N/A
 Dyeing Method: Melt Dyed
 #Colours/Designs: 6/1
 Backing Type: Other
 Felted: N/A
 Spinning System: BCF
 Insect Resist Agent: N/A
 Filament: 23.81
 Master Product:

Test Results:

Pile Mass g/m² (oz/yd²): 1220 (36.0)
 SPM g/m² (oz/yd²): 690 (20.4)
 Stated Pile Height (mm): 4.9
 Minimum Pile Height (mm): 3.9
 Maximum Pile Height (mm): 6.5
 Dynamic Loading Loss (%): 0.0
 Static Loading Loss (%): 0.0
 Tex (g/1000m): 300
 Measured Pile Thickness (mm): 4.7
 Machine Gauge (Tufts/dm): 39.4
 Meas Tufts Perp to Selvedge: 41.7
 Meas Tufts Para to Selvedge: 53.2
 Treated For Soiling Resistance: No
 Soil Resist Inhibitor: No
 Stain Resist Inhibitor: No

Hexapod Scores:

	Texture		Colour		Thickness	
	WA	WA	WA	WA	(mm)	(%)
1500:	4.5	4.5	4.5	4.5	0.4	7.8
8000:	2.5	2.5	3.5	3.5	0.8	18.0

Quality Assurance Test:

Cut Pile (%): 0
 Loop Pile (%): 100
 Panel Assessment Contract: 15
 Panel Assessment Residential: 15
 Suitable For Stairs: Yes
 Tile: Yes SheetGoods: No
 Fibre Signature: NBA:100

ACCS Test:

	Con	Res	Max
SPM/PH Ratio:	16	16	16
Volume Density:	16.8	16.8	20
Tuft Density:	9	9	9
Dyn Load:	3.9	3.9	5
Stat Load:	4.1	4.1	5
Soiling Prop:	12	12	14
Abrasion Res:	10	10	10

Calculations

Pile Height(mm): 5.5
 Tuft Density(per dm²): 2218.4
 GSPM(g/m²): 415.0
 GSPM (abrasive) (g/m²): 275.0
 Soiling Propensity: 12.0 +0.0

OAF Values

OAF: 4.2
 Calc Density (+-5%): 0.14 0.147 0.15
 Base Fibre: NYLON
 Benchmarks:
 RHD1 0 RHD2 3.5
 REHD1 3.5 REHD2 3.5

Environmental Classification:

ECS:

Level:

	Calc	B/M	P/F
Acoustic:	4.7	3	PASS
Thermal:	32	15	PASS
VOC:			
TVOC	0		

Notes:

22/1/24 Submitted by X Translavina. 24/1/2024 Panel graded CEHD(S) 4*.