



# Registration Certificate

Carpet Name: **DECADES**

Licensee: **INTERFACE**

Licence Number: **1016**

Label Number: **23321**

ACCS Contract Grading: **CEHD 4\***

ACCS Residential Grading: **NONE**

Suitable for Stairs: **Yes**

Date Printed: **30/08/2023**



**Andrew Martin**  
Secretary ACCS



Administered by the Carpet Institute of Australia Limited ABN 11 006 829 303

PO Box 7172, St Kilda Road, Melbourne Victoria 8004 Tel: (03) 9804 5559 • Fax: (03) 9804 5560

Email: [info@carpetoz.com.au](mailto:info@carpetoz.com.au) • [www.carpetinstitute.com.au](http://www.carpetinstitute.com.au)

This certificate remains the property of the Carpet Institute of Australia Limited.

**Carpet Details:****Company: INTERFACE****Label No: 23321****Licence No: 1016****Office No: 7430****Names:**

DECADES

**Details:**

Awarded Res Grade: NONE  
 Awarded Con Grade: CEHD 4\*  
 Registered On: 25/08/2023  
 Active: Yes  
 Date In-Active:  
 Manufacture Method: Tufted  
 Twist Set: N/A  
 Dyeing Method: Melt Dyed  
 #Colours/Designs: 12/  
 Backing Type: Other  
 Felted: N/A  
 Spinning System: BCF  
 Insect Resist Agent: N/A  
 Filament: 23.81  
 Master Product:

**Test Results:**

Pile Mass g/m<sup>2</sup> (oz/yd<sup>2</sup>): 1221 (36.0)  
 SPM g/m<sup>2</sup> (oz/yd<sup>2</sup>): 734.19(21.7)  
 Stated Pile Height (mm): 5.1  
 Minimum Pile Height (mm): 4.7  
 Maximum Pile Height (mm): 5.3  
 Dynamic Loading Loss (%): 0.0  
 Static Loading Loss (%): 0.0  
 Tex (g/1000m): 300  
 Measured Pile Thickness (mm): 5.1  
 Machine Gauge (Tufts/dm): 39.4  
 Meas Tufts Perp to Selvedge: 40.0  
 Meas Tufts Para to Selvedge: 37.0  
 Treated For Soiling Resistance: Yes  
 Soil Resist Inhibitor: Yes  
 Stain Resist Inhibitor: Yes

**Hexapod Scores:**

	Texture		Colour		Thickness	
	WA		WA		(mm)	(%)
1500:	4.0	0.0	4.5	0.0	0.6	12.0
8000:	3.0	0.0	4.0	0.0	1.0	20.0

**Quality Assurance Test:**

Cut Pile (%): 0  
 Loop Pile (%): 100  
 Panel Assessment Contract: 16  
 Panel Assessment Residential: 16  
 Suitable For Stairs: Yes  
 Tile: Yes SheetGoods: No  
 Fibre Signature: NBA:100

**ACCS Test:**

	Con	Res	Max
SPM/PH Ratio:	16	16	16
Volume Density:	11.7	11.7	20
Tuft Density:	7.3	7.3	9
Dyn Load:	3.9	3.9	5
Stat Load:	4.1	4.1	5
Soiling Prop:	14	14	16
Abrasion Res:	10	10	10
Sub Total:	67	67	81
Panel Assess:	16	16	19
Total:	83	83	100
Calc Residential Grade:	REHD2		6*
Calc Contract Grade:	CHD		3*

**Calculations**

Pile Height(mm): 8.4  
 Tuft Density(per dm<sup>2</sup>): 1480.0  
 GSPM(g/m<sup>2</sup>): 415.0  
 GSPM (abrasive) (g/m<sup>2</sup>): 275.0  
 Soiling Propensity: 12.0 +2.0

**OAF Values**

OAF: 4.2  
 Calc Density (+-5%): 0.14 0.144 0.15  
 Base Fibre: NYLON  
 Benchmarks:  
 RHD1 0 RHD2 3.5  
 REHD1 3.5 REHD2 3.5

**Environmental Classification:**

ECS:

Level: 0

	Calc	B/M	P/F
Acoustic:	5.1	3	PASS
Thermal:	35.4	15	PASS
VOC:			
TVOC	0		

**Notes:**

25/8/2023 Submitted for ACCS grading by A. Attenborough. 30/8/2023 Tex confirmed at 300. Panel awarded CEHD(S) 4\*.