



Registration Certificate

Carpet Name: **RETROSPEC**

Licensee: **INTERFACE**

Licence Number: **1016**

Label Number: **23325**

ACCS Contract Grading: **CEHD 4***

ACCS Residential Grading: **NONE**

Suitable for Stairs: **Yes**

Date Printed: **30/08/2023**



Andrew Martin
Secretary ACCS



Administered by the Carpet Institute of Australia Limited ABN 11 006 829 303

PO Box 7172, St Kilda Road, Melbourne Victoria 8004 Tel: (03) 9804 5559 • Fax: (03) 9804 5560

Email: info@carpetoz.com.au • www.carpetinstitute.com.au

This certificate remains the property of the Carpet Institute of Australia Limited.

Carpet Details:**Company: INTERFACE****Label No: 23325****Licence No: 1016****Office No: 7434****Names:**

RETROSPEC

Details:

Awarded Res Grade: NONE
 Awarded Con Grade: CEHD 4*
 Registered On: 25/08/2023
 Active: Yes
 Date In-Active:
 Manufacture Method: Tufted
 Twist Set: N/A
 Dyeing Method: Melt Dyed
 #Colours/Designs: 12/
 Backing Type: Other
 Felted: N/A
 Spinning System: BCF
 Insect Resist Agent: N/A
 Filament: 23.81
 Master Product:

Test Results:

Pile Mass g/m² (oz/yd²): 916 (27.0)
 SPM g/m² (oz/yd²): 547.33(16.1)
 Stated Pile Height (mm): 3.8
 Minimum Pile Height (mm): 3.7
 Maximum Pile Height (mm): 3.9
 Dynamic Loading Loss (%): 0.0
 Static Loading Loss (%): 0.0
 Tex (g/1000m): 300
 Measured Pile Thickness (mm): 3.8
 Machine Gauge (Tufts/dm): 39.4
 Meas Tufts Perp to Selvedge: 40.0
 Meas Tufts Para to Selvedge: 34.0
 Treated For Soiling Resistance: Yes
 Soil Resist Inhibitor: Yes
 Stain Resist Inhibitor: Yes

Hexapod Scores:

	Texture		Colour		Thickness	
	WA		WA		(mm)	(%)
1500:	4.0	0.0	4.0	0.0	0.2	5.0
8000:	3.0	0.0	3.5	0.0	0.8	20.0

Quality Assurance Test:

Cut Pile (%): 0
 Loop Pile (%): 100
 Panel Assessment Contract: 16
 Panel Assessment Residential: 16
 Suitable For Stairs: Yes
 Tile: Yes SheetGoods: No
 Fibre Signature: NBA:100

ACCS Test:

	Con	Res	Max
SPM/PH Ratio:	14.2	16	16
Volume Density:	10.7	10.7	20
Tuft Density:	6.7	6.7	9
Dyn Load:	3.9	3.9	5
Stat Load:	4.1	4.1	5
Soiling Prop:	14	14	16
Abrasion Res:	10	10	10
Sub Total:	63.6	65.4	81
Panel Assess:	16	16	19
Total:	79.6	81.4	100
Calc Residential Grade:	REHD2		6*
Calc Contract Grade:	CHD		3*

Calculations

Pile Height(mm): 6.8
 Tuft Density(per dm²): 1360.0
 GSPM(g/m²): 415.0
 GSPM (abrasive) (g/m²): 275.0
 Soiling Propensity: 12.0 +2.0

OAF Values

OAF: 4.2
 Calc Density (+-5%): 0.14 0.144 0.15
 Base Fibre: NYLON
 Benchmarks:
 RHD1 0 RHD2 3.5
 REHD1 3.5 REHD2 3.5

Environmental Classification:

ECS:

Level: 0

	Calc	B/M	P/F
Acoustic:	3.8	3	PASS
Thermal:	26.4	15	PASS
VOC:			
TVOC	0		

Notes:

25/8/2023 Submitted for ACCS grading by A. Attenborough. 30/8/2023 Tex confirmed at 300. Panel awarded CEHD(S) 4*.