WTA Product Testing

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N. 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O. Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

CLIENT : INTERFACE AUSTRALIA PTY LTD

34 AIRDS ROAD MINTO NSW 2566 TEST NUMBER ISSUE DATE PRINT DATE

: 7-598559-AN : 22/07/2014 : 22/07/2014

SAMPLE DESCRIPTION Clients Ref: "HN 850"

Cut & Loop pile carpet tile

Colour: Multicolour Approx pile height: 8mm

Material Specification:

Nominal pile composition: 100% recycled type yarn Nylon 6

Nominal total pile mass: 1085g/m2

Nominal backing: Glasbac

ASISO 9239.1-2003

Reaction to Fire Tests for Floorings Determination of the Burning Behaviour

using a Radiant Heat Source

198

Date of sample arrival: Date tested:

Results:

Length

10/06/2014 22/07/2014

CHF Value

215

5.9 Length Width 6.3

Mean 6.1 4.9 kW/m2 5.6 kW/m2

217

% min

Smoke Value

Width

238 % min Observations: melting, blistering

Note: Sample was conditioned in accordance with BSEN 13238-2001 at a temperature of 23+/-2degC and Relative Humidity of 50+/-5% for a minimum of 48 hurs prior to testing

Each specimen was adhered to a substrate of 6mm fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use

207617 END OF REPORT PAGE 1

© Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for:
-Chemical Testing of Textiles & Related Products : Accreditation No. 983
-Mechanical Testing of Textiles & Related Products : Accreditation No. 985
-Heat & Temperature Measurement : Accreditation No. 1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if ammended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.

HAEL A. JACKSON B.Sc.(Hons)

LIMITED