

SYDNEY CARPET LABORATORY

34 AIRDS ROAD, MINTO NSW 2566 - TEL: (02) 8706 4600 FAX: (02) 8706 4617

TEST REPORT

Client: Interface Australia PTY LTD 34 Airds Road Minto NSW 2566 Test Report No: R20-159 Sample Received date: 19/08/2020 Test Date: 25/08/2020 Report Date: 27/08/2020

Sample Description: Client Reference: "OLD ST" 100% Solution Dyed Nylon 66 610g/m2 on a Glasbac Backing

AS ISO 9239.1: Reaction to Fire Tests for Floorings – Determination of the Burning Behaviour Using a Radiant Heat Source

Results Summary

| CHF Value | Sample 1 | Sample 2 | Sample 3 | Mean | |
|-----------|----------|----------|----------|------|-------------------|
| Length | 5.3 | 5.3 | 5.1 | 5.2 | kW/m² |
| Width | 5.5 | - | - | - | kW/m ² |

| Smoke Value | Sample 1 | Sample 2 | Sample 3 | Mean | |
|-------------|----------|----------|----------|------|-------|
| Length | 166 | 162 | 164 | 164 | %.min |
| Width | 168 | - | - | - | %.min |

| Melting | Yes |
|------------|-----|
| Blistering | Yes |

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BS EN 13238 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Each Specimen was adhered to a substrate of 9mm thick fibre cement board using Intertac adhesive.

END OF REPORT

Accreditation No.2834.

Page 1 of 1

Accredited for compliance with ISO/IEC 17025 - Testing

The results of the test, calibrations and/or measurements included in this document are traceable to Australian/ International Standards. This report may not be reproduced except in full and shall be rendered void if amended or altered.

This document may not be used in any form without prior consent. The results on this report are related only to the items tested.