

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

34 Airds Ro			Issue		21-00121 22/04/202	21	
Minto NSW	2566			Date : Number :	4/05/2021 PO 12794		
Sample Description	•	tion Dyed Nylo		De chie e			
	Nominal Mass per Unit Area/Density : 712g/m2 on a Glasbac Backing						
S ISO 9239.1-2003	Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source						
	Date of Sample Arrival		12-03-2	021			
	Date Tested 22-04-2021						
	CHF Value	1	2	3	Mean		
	Length	3.8	4.1	3.9	3.9	kW/m²	
	Width	4.6	-	-	-	kW/m²	
	HF-30 Value	1	2	3	Mean		
	Length	4.1	4.6	4.3	4.3	kW/m²	
	Width	5.7	-	-	-	kW/m²	
	Smoke Value	1	2	3	Mean		
	Length	251	243	224	239	%.min	
	Width	221	-	-	-	%.min	
	Melting				Yes		

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



NATA



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

1. . e. Chris Campbell

APPROVED SIGNATORY



Page 1 of 2

MICHAEL A. JACKSON B.Sc.(Hons)

C



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client :	Interface Australia Pty Ltd	Test Number :	21-001211
	34 Airds Road	Issue Date :	22/04/2021
	Minto NSW 2566	Print Date :	4/05/2021
		Order Number :	PO 127944

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing.

236129

50348

C Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

1.5 Chris Campbell

APPROVED SIGNATORY





